

**BLOME INTERNATIONAL** 

1450 HOFF INDUSTRIAL DRIVE O' FALLON, MO 63366

Telephone: 610-345-0037 ◆ FAX: 610-345-0038

Surrounding You with Exceptional Protection™

## **TECHNICAL DATA – FULLY VITRIFIED CERAMIC TILE**

Material: Fully Vitrified Ceramic Tiles, unglazed, dry pressed

Fire-sealed (according to ISO 10545, 1-17)

Collection: ZF - 100x200x18mm (4"x 8"x 3/4"),

ZF - 100x18mm (4"x 3/4") Hexagon

Surface: R11, R12, R13

Colors: plain, speckled, mottled, red



Porsche color shown above

| Dimension and flatness       | Standard Values           | DIN / EN  | VERSI-TILE™ Fully-Vitrified Ceramics                |
|------------------------------|---------------------------|-----------|---|
| 1. Length and Width          | ± 0.75 %                  | EN 98     | VERSI-TILE™ Fully-vitrified tiles fulfill or exceed |
| 2. Width                     | ± 0.75 %                  | EN 98     | the requirements for dimensional tolerance          |
| 3. Thickness                 | ± 5.0 %                   | EN 98     | and flatness according to all relevant              |
| 4. Edge deviation            | ± 0.5 %                   | EN 98     | DIN / EN / ISO standards.                           |
| Physical Properties          |                           |           |   |
| 1. Water Absorption          | max, 0.5%                 | EN 99     | 0.1% < 0.5%   |
| 2. Bending Strength          | min, 27 N/mm <sup>2</sup> | EN 100    | > 51 N/mm²  |
| 3. Impact Resistance         | 5,800 N                   | EN 100    | > 8,200 N   |
| 4. Frost Resistance          | Required                  | EN 202    | Fulfilled   |
| 5. Hardness (MOH)            | 6                         | EN 101    | 7   |
| 6. Deep Abrasion Resistance  | max, < 205mm <sup>3</sup> | EN 102    | < 141mm³  |
| 7. Compressive Strength      | 150 N/mm <sup>2</sup>     | DIN 18158 | > 340 N/mm <sup>2</sup>                             |
| 8. Light and Color Stability | Required                  | DIN 51094 | Fulfilled   |
| 9. Resistance to Fire        | non-combustible           | DIN 4102  | Fulfilled   |
| 10. Chemical Resistance      | min, Class B              | EN 106    | Fulfilled   |
| 11. Shade Variation (Color)  | V1,V2,V3,V4               | INDUSTRY  | ≤ V2  |

Since 1975, Blome International has been a trusted supplier of heavy-duty, durable, corrosion resistant and antimicrobial protective linings for floors, walls, storage and feed tanks, and secondary containment systems. Our extensive experience providing targeted solutions to the Food and Beverage Industry qualifies us to take on your most challenging problems. Blome International materials and engineered solutions are currently employed in some of the most difficult and aggressive environments with outstanding results and unparalleled life-cycle economics. VERSI-TILE<sup>TM</sup> Fully Vitrified Tiles exceed industry standards for performance and quality. Call Blome International today for an independent consultation to discuss the needs and requirements of your facility and how to convert your infrastructure linings from a liability to a low-cost asset.

Blome International 1450 Hoff Industrial Blvd. O' Fallon, MO 63366



Telephone: (610) 345-0037 Fax: (610) 345-0038 www.blome.com